



## Standard Specification for Titanium and Titanium Alloy Bars and Billets<sup>1</sup>

This standard is issued under the fixed designation B 348; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification<sup>2</sup> covers annealed titanium and titanium alloy bars and billets as follows:

1.1.1 *Grade 1*—Unalloyed titanium,

1.1.2 *Grade 2*—Unalloyed titanium,

1.1.2.1 *Grade 2H*—Unalloyed titanium (Grade 2 with 58 ksi minimum UTS),

1.1.3 *Grade 3*—Unalloyed titanium,

1.1.4 *Grade 4*—Unalloyed titanium,

1.1.5 *Grade 5*—Titanium alloy (6 % aluminum, 4 % vanadium),

1.1.6 *Grade 6*—Titanium alloy (5 % aluminum, 2.5 % tin),

1.1.7 *Grade 7*—Unalloyed titanium plus 0.12 to 0.25 % palladium,

1.1.7.1 *Grade 7H*—Unalloyed titanium plus 0.12 to 0.25 % palladium (Grade 7 with 58 ksi minimum UTS),

1.1.8 *Grade 9*—Titanium alloy (3 % aluminum, 2.5 % vanadium),

1.1.9 *Grade 11*—Unalloyed titanium plus 0.12 to 0.25 % palladium,

1.1.10 *Grade 12*—Titanium alloy (0.3 % molybdenum, 0.8 % nickel),

1.1.11 *Grade 13*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),

1.1.12 *Grade 14*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),

1.1.13 *Grade 15*—Titanium alloy (0.5 % nickel, 0.05 % ruthenium),

1.1.14 *Grade 16*—Unalloyed titanium plus 0.04 to 0.08 % palladium,

1.1.14.1 *Grade 16H*—Unalloyed titanium plus 0.04 to 0.08 % palladium (Grade 16 with 58 ksi minimum UTS),

1.1.15 *Grade 17*—Unalloyed titanium plus 0.04 to 0.08 % palladium,

1.1.16 *Grade 18*—Titanium alloy (3 % aluminum, 2.5 % vanadium) plus 0.04 to 0.08 % palladium,

1.1.17 *Grade 19*—Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum),

1.1.18 *Grade 20*—Titanium alloy (3 % aluminum, 8 % vanadium, 6 % chromium, 4 % zirconium, 4 % molybdenum) plus 0.04 %–0.08 % palladium,

1.1.19 *Grade 21*—Titanium alloy (15 % molybdenum, 3 % aluminum, 2.7 % niobium, 0.25 % silicon),

1.1.20 *Grade 23*—Titanium alloy (6 % aluminum, 4 % vanadium with extra low interstitial elements, ELI),

1.1.21 *Grade 24*—Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.04 % to 0.08 % palladium,

1.1.22 *Grade 25*—Titanium alloy (6 % aluminum, 4 % vanadium) plus 0.3 % to 0.8 % nickel and 0.04 % to 0.08 % palladium,

1.1.23 *Grade 26*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium,

1.1.23.1 *Grade 26H*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium (Grade 26 with 58 ksi minimum UTS),

1.1.24 *Grade 27*—Unalloyed titanium plus 0.08 to 0.14 % ruthenium,

1.1.25 *Grade 28*—Titanium alloy (3 % aluminum, 2.5 % vanadium plus 0.08–0.14 % ruthenium),

1.1.26 *Grade 29*—Titanium alloy (6 % aluminum, 4 % vanadium, extra low interstitial, ELI plus 0.08–0.14 % ruthenium),

1.1.27 *Grade 30*—Titanium alloy (0.3 % cobalt, 0.05 % palladium),

1.1.28 *Grade 31*—Titanium alloy (0.3 % cobalt, 0.05 % palladium),

1.1.29 *Grade 32*—Titanium alloy (5 % aluminum, 1 % tin, 1 % zirconium, 1 % vanadium, 0.8 % molybdenum),

1.1.30 *Grade 33*—Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),

1.1.31 *Grade 34*—Titanium alloy (0.4 % nickel, 0.015 % palladium, 0.025 % ruthenium, 0.15 % chromium),

1.1.32 *Grade 35*—Titanium alloy (4.5 % aluminum, 2 % molybdenum, 1.6 % vanadium, 0.5 % iron, 0.3 % silicon),

1.1.33 *Grade 36*—Titanium alloy (45 % niobium),

1.1.34 *Grade 37*—Titanium alloy (1.5 % aluminum), and

1.1.35 *Grade 38*—Titanium alloy (4 % aluminum, 2.5 % vanadium, 1.5 % iron).

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.01 on Titanium.

Current edition approved June 1, 2006. Published June 2006. Originally approved in 1959. Last previous edition approved in 2006 as B 348 – 06.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SB-348 in Section II of that Code.

NOTE 1—H grade material is identical to the corresponding numeric grade (that is, Grade 2H = Grade 2) except for the higher guaranteed

minimum UTS, and may always be certified as meeting the requirements of its corresponding numeric grade. Grades 2H, 7H, 16H, and 26H are intended primarily for pressure vessel use.

The H grades were added in response to a user association request based on its study of over 5200 commercial Grade 2, 7, 16, and 26 test reports, where over 99 % met the 58 ksi minimum UTS.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

2.1 ASTM Standards: <sup>3</sup>

- E 8 Test Methods for Tension Testing of Metallic Materials
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

E 120 Test Methods for Chemical Analysis of Titanium and Titanium Alloys<sup>4</sup>

E 1409 Test Method for Determination of Oxygen and Nitrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique

E 1447 Test Method for Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity/Infrared Detection Method

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *bar, n*—a hot rolled, forged, or cold worked semifinished solid section product whose cross sectional area is equal to or less than 16 in.<sup>2</sup>(10 323 mm<sup>2</sup>); rectangular bar must be less than or equal to 10 in. (254 mm) in width and greater than 0.1875 in. (4.8 mm) in thickness.

3.1.2 *billet, n*—a solid semifinished section hot rolled or forged from an ingot, with a cross sectional area greater than 16 in.<sup>2</sup>(10 323 mm<sup>2</sup>) whose width is less than five times its thickness.

<sup>4</sup> Withdrawn.

TABLE 1 Chemical Requirements<sup>A</sup>

Element	Composition, %											
	Grade 1	Grade 2	Grade 2H	Grade 3	Grade 4	Grade 5	Grade 6	Grade 7	Grade 7H	Grade 9	Grade 11	Grade 12
Nitrogen, max	0.03	0.03	0.03	0.05	0.05	0.05	0.03	0.03	0.03	0.03	0.03	0.03
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08
Hydrogen, <sup>B,C</sup> max	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.015
Iron, max	0.20	0.30	0.30	0.30	0.50	0.40	0.50	0.30	0.30	0.25	0.20	0.30
Oxygen, max	0.18	0.25	0.25	0.35	0.40	0.20	0.20	0.25	0.25	0.15	0.18	0.25
Aluminum	...	...	...	...	...	5.5-6.75	4.0-6.0	...	...	2.5-3.5	...	...
Vanadium	...	...	...	...	...	3.5-4.5	...	...	...	2.0-3.0	...	...
Tin	...	...	...	...	...	...	2.0-3.0	...	...	...	...	...
Ruthenium	...	...	...	...	...	...	...	...	...	...	...	...
Palladium	...	...	...	...	...	...	...	0.12-0.25	0.12-0.25	...	0.12-0.25	...
Cobalt	...	...	...	...	...	...	...	...	...	...	...	...
Molybdenum	...	...	...	...	...	...	...	...	...	...	...	0.2-0.4
Chromium	...	...	...	...	...	...	...	...	...	...	...	...
Nickel	...	...	...	...	...	...	...	...	...	...	...	0.6-0.9
Niobium	...	...	...	...	...	...	...	...	...	...	...	...
Zirconium	...	...	...	...	...	...	...	...	...	...	...	...
Silicon	...	...	...	...	...	...	...	...	...	...	...	...
Residuals, <sup>D,E,F</sup> max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Residuals, <sup>D,E,F</sup> max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Titanium <sup>G</sup>	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance

Element	Composition, %										
	Grade 13	Grade 14	Grade 15	Grade 16	Grade 16H	Grade 17	Grade 18	Grade 19	Grade 20	Grade 21	
Nitrogen, max	0.03	0.03	0.05	0.03	0.03	0.03	0.03	0.03	0.03	0.03	
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.05	0.05	0.05	
Hydrogen, <sup>B,C</sup> max	0.015	0.015	0.015	0.015	0.015	0.015	0.015	0.02	0.02	0.015	
Iron, max	0.20	0.30	0.30	0.30	0.30	0.20	0.25	0.30	0.30	0.40	
Oxygen, max	0.10	0.15	0.25	0.25	0.25	0.18	0.15	0.12	0.12	0.17	
Aluminum	...	...	...	...	...	...	2.5-3.5	3.0-4.0	3.0-4.0	2.5-3.5	
Vanadium	...	...	...	...	...	...	2.0-3.0	7.5-8.5	7.5-8.5	...	
Tin	...	...	...	...	...	...	...	...	...	...	
Ruthenium	0.04-0.06	0.04-0.06	0.04-0.06	...	...	...	...	...	...	...	
Palladium	...	...	...	0.04-0.08	0.04-0.08	0.04-0.08	0.04-0.08	...	0.04-0.08	...	
Cobalt	...	...	...	...	...	...	...	...	...	...	
Molybdenum	...	...	...	...	...	...	...	3.5-4.5	3.5-4.5	14.0-16.0	
Chromium	...	...	...	...	...	...	...	5.5-6.5	5.5-6.5	...	
Nickel	0.4-0.6	0.4-0.6	0.4-0.6	...	...	...	...	...	...	...	

Ni  
Zir  
Sil  
Re  
eac  
Re  
tot  
Tit  
  
 N  
C  
H  
In  
O  
A  
V  
T  
R  
P  
C  
M  
C  
N  
N  
Z  
S  
R  
e  
F  
t  
T

Element	Composition, %									
	Grade 13	Grade 14	Grade 15	Grade 16	Grade 16H	Grade 17	Grade 18	Grade 19	Grade 20	Grade 21
Niobium	...	...	...	...	...	...	...	...	...	2.2-3.2
Zirconium	...	...	...	...	...	...	...	3.5-4.5	3.5-4.5	...
Silicon	...	...	...	...	...	...	...	...	...	0.15-0.25
Residuals, <sup>D,E,F</sup> max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.15	0.15	0.1
Residuals, <sup>D,E,F</sup> max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Titanium <sup>G</sup>	balance	balance	balance	balance	balance	balance	balance	balance	balance	balance

Element	Composition, %									
	Grade 23	Grade 24	Grade 25	Grade 26	Grade 26H	Grade 27	Grade 28	Grade 29	Grade 30	
Nitrogen, max	0.03	0.05	0.05	0.03	0.03	0.03	0.03	0.03	0.03	
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	0.08	
Hydrogen, <sup>B,C</sup> max	0.0125	0.015	0.0125	0.015	0.015	0.015	0.015	0.015	0.015	
Iron, max	0.25	0.40	0.40	0.30	0.30	0.20	0.25	0.25	0.30	
Oxygen, max	0.13	0.20	0.20	0.25	0.25	0.18	0.15	0.13	0.25	
Aluminum	5.5-6.5	5.5-6.75	5.5-6.75	...	...	...	2.5-3.5	5.5-6.5	...	
Vanadium	3.5-4.5	3.5-4.5	3.5-4.5	...	...	...	2.0-3.0	3.5-4.5	...	
Tin	...	...	...	...	...	...	...	...	...	
Ruthenium	...	...	...	0.08-0.14	0.08-0.14	0.08-0.14	0.08-0.14	0.08-0.14	...	
Palladium	...	0.04-0.08	0.04-0.08	...	...	...	...	...	0.04-0.08	
Cobalt	...	...	...	...	...	...	...	...	0.20-0.80	
Molybdenum	...	...	...	...	...	...	...	...	...	
Chromium	...	...	...	...	...	...	...	...	...	
Nickel	...	...	0.3-0.8	...	...	...	...	...	...	
Niobium	...	...	...	...	...	...	...	...	...	
Zirconium	...	...	...	...	...	...	...	...	...	
Silicon	...	...	...	...	...	...	...	...	...	
Residuals, <sup>D,E,F</sup> max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	
Residuals, <sup>D,E,F</sup> max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	
Titanium <sup>G</sup>	balance	balance	balance	balance	balance	balance	balance	balance	balance	

Element	Composition, %								
	Grade 31	Grade 32	Grade 33	Grade 34	Grade 35	Grade 36	Grade 37	Grade 38	
Nitrogen, max	0.05	0.03	0.03	0.05	0.05	0.03	0.03	0.03	
Carbon, max	0.08	0.08	0.08	0.08	0.08	0.04	0.08	0.08	
Hydrogen, <sup>B,C</sup> max	0.015	0.015	0.015	0.015	0.015	0.0035	0.015	0.015	
Iron, max or range	0.30	0.25	0.30	0.30	0.20-0.80	0.03	0.30	1.2-1.8	
Oxygen, max or range	0.35	0.11	0.25	0.35	0.25	0.16	0.25	0.20-0.30	
Aluminum	...	4.5-5.5	...	...	4.0-5.0	...	1.0-2.0	3.5-4.5	
Vanadium	...	0.6-1.4	...	...	1.1-2.1	...	...	2.0-3.0	
Tin	...	0.6-1.4	...	...	...	...	...	...	
Ruthenium	...	...	0.02-0.04	0.02-0.04	...	...	...	...	
Palladium	0.04-0.08	...	0.01-0.02	0.01-0.02	...	...	...	...	
Cobalt	0.20-0.80	...	...	...	...	...	...	...	
Molybdenum	...	0.6-1.2	...	...	1.5-2.5	...	...	...	
Chromium	...	...	0.1-0.2	0.1-0.2	...	...	...	...	
Nickel	...	...	0.35-0.55	0.35-0.55	...	...	...	...	
Niobium	...	...	...	...	...	42.0-47.0	...	...	
Zirconium	...	0.6-1.4	...	...	...	...	...	...	
Silicon	...	0.06-0.14	...	...	0.20-0.40	...	...	...	
Residuals, <sup>D,E,F</sup> max each	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1	
Residuals, <sup>D,E,F</sup> max total	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	
Titanium <sup>G</sup>	balance	balance	Remainder	Remainder	Remainder	Remainder	Remainder	balance	

<sup>A</sup> Analysis shall be completed for all elements listed in this table for each grade. The analysis results for the elements not quantified in the table need not be reported unless the concentration level is greater than 0.1 % each or 0.4 % total.

<sup>B</sup> Lower hydrogen may be obtained by negotiation with the manufacturer.

<sup>C</sup> Final product analysis.

<sup>D</sup> Need not be reported.

<sup>E</sup> A residual is an element present in a metal or an alloy in small quantities and is inherent to the manufacturing process but not added intentionally. In titanium these elements include aluminum, vanadium, tin, chromium, molybdenum, niobium, zirconium, hafnium, bismuth, ruthenium, palladium, yttrium, copper, silicon, cobalt, tantalum, nickel, boron, manganese, and tungsten.

<sup>F</sup> The purchaser may, in his written purchase order, request analysis for specific residual elements not listed in this specification.

<sup>G</sup> The percentage of titanium is determined by difference.



## 5. Chemical Composition

5.1 The grades of titanium and titanium alloy metal covered by this specification shall conform to the requirements as to chemical composition prescribed in Table 1.

5.1.1 The elements listed in Table 1 are intentional alloy additions or elements which are inherent to the manufacture of titanium sponge, ingot or mill product.

5.1.1.1 Elements other than those listed in Table 1 are deemed to be capable of occurring in the grades listed in Table 1 by and only by way of unregulated or unanalyzed scrap additions to the ingot melt. Therefore, product analysis for elements not listed in Table 1 shall not be required unless specified and shall be considered to be in excess of the intent of this specification.

5.1.2 Elements intentionally added to the melt must be identified, analyzed and reported in the chemical analysis.

5.2 When agreed upon by the producer and purchaser and requested by the purchaser in his written purchase order, chemical analysis shall be completed for specific residual elements not listed in this specification.

5.3 *Product Analysis*—Product analysis tolerances do not broaden the specified heat analysis requirements, but cover variations between laboratories in the measurement of chemical content. The manufacturer shall not ship material which is outside the limits specified in Table 1 for the applicable grade. Product analysis limits shall be as specified in Table 3.

**TABLE 3 Permissible Variations in Product Analysis**

Element	Product Analysis Limits, max or Range, %	Permissible Variation in Product Analysis
Aluminum	0.5 to 2.5	±0.20
Aluminum	2.5 to 6.75	±0.40
Carbon	0.10	+ 0.02
Chromium	0.1 to 0.2	±0.02
Chromium	5.5 to 6.5	±0.30
Cobalt	0.2 to 0.8	±0.05
Hydrogen	0.02	+ 0.002
Iron	0.80	+ 0.15
Iron	1.2 to 1.8	±0.20
Molybdenum	0.2 to 0.4	±0.03
Molybdenum	0.6 to 1.2	±0.15
Molybdenum	1.5 to 4.5	±0.20
Molybdenum	14.0 to 16.0	±0.50
Nickel	0.3 to 0.9	±0.05
Niobium	2.2 to 3.2	±0.15
Niobium	>30	±0.50
Nitrogen	0.05	+ 0.02
Oxygen	0.30	+ 0.03
Oxygen	0.31 to 0.40	±0.04
Palladium	0.01 to 0.02	±0.002
Palladium	0.04 to 0.08	±0.005
Palladium	0.12 to 0.25	±0.02
Ruthenium	0.02 to 0.04	±0.005
Ruthenium	0.04 to 0.06	±0.005
Ruthenium	0.08 to 0.14	±0.01
Silicon	0.06 to 0.40	±0.02
Tin	0.62.0 to 3.0	±0.15
Vanadium	0.6 to 4.5	±0.15
Vanadium	7.5 to 8.5	±0.40
Zirconium	0.6 to 1.4	±0.15
Residuals <sup>A</sup> (each)	0.15	+ 0.02

<sup>A</sup> A residual is an element present in a metal or alloy in small quantities and is inherent to the manufacturing process but not added intentionally. In titanium these elements include aluminum, vanadium, tin, iron, chromium, molybdenum, niobium, zirconium, hafnium, bismuth, ruthenium, palladium, yttrium, copper, silicon, cobalt, tantalum, nickel, boron, manganese, and tungsten.

## 6. Mechanical Properties

6.1 Material supplied under this specification shall conform to the mechanical property requirements given in Table 2, as applicable.

6.2 Tension testing specimens are to be machined and tested in accordance with Test Methods E 8. Tensile properties shall be determined using a strain rate of 0.003 to 0.007 in./in./min through the specified yield strength, and then increasing the rate so as to produce failure in approximately one additional minute.

## 7. Dimensions, Weight, and Permissible Variations

7.1 *Size*—Tolerances on titanium and titanium alloy material covered by this specification shall be as specified in Tables 4-11, as applicable.

7.2 *Weight*—Quantity extras are applicable to individual items of a grade, thickness, width, and length ordered at one time for shipment at one time to one destination. Different lengths of the same size and grade may be combined for quantity extra. The shipping weight of any item of an ordered size in any finish may exceed the theoretical weight by as much as 10 %.

## 8. Workmanship, Finish, and Appearance

8.1 Titanium and titanium alloy bar and billet shall be free of injurious external and internal imperfections of a nature that will interfere with the purpose for which it is intended. Annealed material may be furnished as descaled, sandblasted, ground, or rough turned. The manufacturer shall be permitted to remove minor surface imperfections by spot grinding if such grinding does not reduce the thickness of the material below the minimum permitted by the tolerance for the thickness ordered.

## 9. Sampling

9.1 Samples for chemical analyses shall be representative of the material being tested. The utmost care must be used in sampling titanium for chemical analysis because of its great affinity for elements such as oxygen, nitrogen, and hydrogen. Therefore, in cutting samples for analysis, the operation should be carried out insofar as possible in a dust-free atmosphere. Chips should be collected from clean metal and tools should be clean and sharp. Samples for analysis should be stored in suitable containers.

9.2 At least two samples for chemical analysis shall be tested to determine chemical composition. Samples shall be taken from the ingot or from the opposite extremes of the product to be analyzed.

## 10. Methods of Chemical Analysis

10.1 The chemical analysis shall be conducted by the standard techniques normally utilized by the manufacturer and the purchaser. In case of disagreement Test Methods E 120 shall be used as the referee method except for carbon, oxygen, and hydrogen which are not covered in Test Methods E 120. Test Method E 1409 shall be used as a referee method for oxygen and Test E 1447 shall be used as a referee method for hydrogen.

**TABLE 4 Permissible Variations in Size for Titanium Bars—Hot-Rolled Rounds and Squares**

Specified Size, in. (mm)	Size Variations, in. (mm)	Out-of-Round <sup>A</sup> or Out-of-Square, <sup>B</sup> in. (mm)
¼ to ⅝ (6.35 to 7.94), incl	±0.005 (0.13)	0.008 (0.20)
Over ⅝ to ⅞ (7.94 to 11.11), incl	±0.006 (0.15)	0.009 (0.23)
Over ⅞ to 1 (11.11 to 15.88), incl	±0.007 (0.18)	0.010 (0.25)
Over 1 to 1 ⅛ (15.88 to 22.22), incl	±0.008 (0.20)	0.012 (0.30)
Over 1 ⅛ to 1 ¼ (22.22 to 25.40), incl	±0.009 (0.23)	0.013 (0.33)
Over 1 ¼ to 1 ½ (25.40 to 28.58), incl	±0.010 (0.25)	0.015 (0.38)
Over 1 ½ to 1 ¾ (28.58 to 31.75), incl	±0.011 (0.28)	0.016 (0.41)
Over 1 ¾ to 1 ⅞ (31.75 to 34.92), incl	±0.012 (0.30)	0.018 (0.46)
Over 1 ⅞ to 2 (34.92 to 38.10), incl	±0.014 (0.36)	0.021 (0.53)
Over 2 to 2 ¼ (38.10 to 50.80), incl	± ⅞₆₄ (0.40)	0.023 (0.58)
Over 2 ¼ to 2 ½ (50.80 to 63.50), incl	+ ⅞₆₄, - 0 (0.79)	0.023 (0.58)
Over 2 ½ to 3 (63.50 to 88.90), incl	+ ⅜₆₄, - 0 (1.19)	0.035 (0.89)
Over 3 to 3 ½ (88.90 to 114.30), incl	+ ⅜₆₄, - 0 (1.59)	0.046 (1.17)

<sup>A</sup> Out-of-round is the difference between the maximum and minimum diameters of the bar, measured at the same cross section.

<sup>B</sup> Out-of-square section is the difference in the two dimensions at the same cross section of a square bar, each dimension being the distance between opposite faces.

**TABLE 5 Permissible Variations in Size for Titanium Bars—Hot-Rolled Hexagons and Octagons**

Specified Sizes Between Opposite Sides, in. (mm)	Size Variation, in. (mm)	Maximum Difference, 3 Measurements, in. (mm)
¼ to ½ (6.35 to 12.70), incl	±0.007 (0.18)	0.011 (0.28)
Over ½ to 1 (12.70 to 25.40), incl	±0.010 (0.25)	0.015 (0.38)
Over 1 to 1 ½ (25.40 to 38.10), incl	±0.021 (0.53)	0.025 (0.64)
Over 1 ½ to 2 (38.10 to 50.80), incl	± ⅞₆₄ (0.79)	⅞₆₄ (0.79)
Over 2 to 2 ½ (50.80 to 63.50), incl	± ⅜₆₄ (1.19)	⅜₆₄ (1.19)
Over 2 ½ to 3 (63.50 to 88.90), incl	± ⅜₆₄ (1.59)	⅜₆₄ (1.59)

**TABLE 6 Permissible Variations in Size for Titanium Bars—Hot-Rolled Flats**

Specified Widths, in. (mm)	Thickness Variation from Specified Thickness, in. (mm)			Width Variation, in. (mm)
	⅞ to ½ in. (3.18 to 12.70 mm), incl	Over ½ to 1 in. (12.70 to 25.40 mm), incl	Over 1 to 2 in. (25.40 to 50.80 mm), incl	
To 1 (25.40), incl	±0.008 (0.20)	±0.010 (0.25)	...	+ ⅞₆₄, - ⅞₆₄ (+ 0.40, - 0.40)
Over 1 to 2 (25.40 to 50.80), incl	±0.012 (0.30)	±0.015 (0.38)	± ⅞₆₄ (0.79)	+ ⅞₆₄, - ⅞₆₄ (+ 0.79, - 0.79)
Over 2 to 4 (50.80 to 101.60), incl	±0.015 (0.38)	±0.020 (0.51)	± ⅞₆₄ (0.79)	+ ⅞₆₄, - ⅞₆₄ (+ 1.59, - 0.79)
Over 4 to 6 (101.60 to 152.40), incl	±0.015 (0.38)	±0.020 (0.51)	± ⅞₆₄ (0.79)	+ ⅞₆₄, - ⅞₆₄ (+ 2.38, - 1.59)
Over 6 to 8 (152.40 to 203.20), incl	±0.016 (0.41)	±0.025 (0.64)	± ⅞₆₄ (0.79)	+ ⅞₆₄, - ⅞₆₄ (+ 3.18, - 3.97)
Over 8 to 10 (203.20 to 254.0), incl	±0.021 (0.53)	±0.031 (0.79)	± ⅞₆₄ (0.79)	+ ⅞₆₄, - ⅞₆₄ (+ 3.97, - 4.76)

**TABLE 7 Permissible Variations in Size for Titanium Bars—Cold-Finished Rounds**

Specified Size, in. (mm)	Size Variation, <sup>A</sup> in. (mm)
Over ½ to 1 (12.70 to 25.40), excl	±0.002 (0.05)
1 to 1 ½ (25.40 to 38.10), excl	±0.0025 (0.06)
1 ½ to 4 (38.10 to 101.60), incl	±0.003 (0.08)

<sup>A</sup> When it is necessary to heat treat or heat treat and pickle after cold finishing, because of special hardness or mechanical property requirements, tolerances are commonly double those shown in this table.

**TABLE 8 Permissible Variations in Size for Titanium Bars—Cold-Finished Hexagons, Octagons, and Squares**

Specified Size, in. (mm)	Size Variation, <sup>A</sup> in. (mm)
Over ½ to 1 (12.70 to 25.40), incl	+ 0, - 0.004 (-0.10)
Over 1 to 2 (25.40 to 50.80), incl	+ 0, - 0.006 (-0.16)
Over 2 to 3 (50.80 to 76.20), incl	+ 0, - 0.008 (-0.20)
Over 3 (76.20)	+ 0, - 0.010 (-0.25)

**11. Retests**

11.1 If the results of any chemical or mechanical property test lot are not in conformance with the requirements of this specification, the lot may be retested at the option of the

manufacturer. The frequency of the retest will double the initial number of tests. If the results of the retest conform to the specification, then the retest values will become the test values for certification. Only original conforming test results or the

Size Wi  
Over ¾  
Over 1  
Over 2  
Over 3  
When  
common  
To 2 (5  
Over 2  
Over 4  
Over 6  
Over 9  
To 3 (7  
Over 3  
Over 6  
Over 9  
TAB  
Non  
Measu  
Unless  
ing pu  
fed in  
Hot roll  
Cold fir  
confo  
the re  
mater  
12. F  
12.  
and t  
requi  
cree  
shall  
this s  
Su  
13. F  
13.  
speci  
value  
right-  
value  
Practi

TABLE 9 Permissible Variations in Size for Titanium Bars—Cold-Finished Flats

Size Width or Thickness, in. (mm)	Width Variations <sup>A</sup> from Specified Thicknesses, in. (mm)		Thickness Variation, <sup>A</sup> in. (mm)
	¼ in. (6.35 mm) and under	Over ¼ in. (6.35 mm)	
Over ¾ to 1 (9.54 to 25.40), incl	±0.004 (0.10)	±0.002 (0.05)	±0.002 (0.05)
Over 1 to 2 (25.40 to 50.80), incl	±0.006 (0.15)	±0.003 (0.08)	±0.003 (0.08)
Over 2 to 3 (50.80 to 76.20), incl	±0.008 (0.20)	±0.004 (0.10)	±0.004 (0.10)
Over 3 to 4½ (76.20 to 114.30), incl	±0.010 (0.25)	±0.005 (0.13)	±0.005 (0.13)

<sup>A</sup>When it is necessary to heat treat or heat treat and pickle after cold finishing, because of special hardness or mechanical property requirements, tolerances are commonly double those shown in this table.

TABLE 10 Permissible Variations in Length for Titanium Bars—Hot Rolled and Cold Finished

Specified Sizes, all Shapes, in. (mm)	Length Variations, in. (mm)	
	To 12 ft (3.66 m), incl	Over 12 to 25 ft (3.66 to 7.62 m), incl
Over 2 (50.80), incl	+ ½, - 0 (+ 12.70)	+ ¾, - 0 (+ 19.05)
Over 2 to 4 (50.80 to 101.60), incl	+ ¾, - 0 (+ 19.05)	+ 1, - 0 (+ 25.40)
Over 4 to 6 (101.60 to 152.40), incl	+ 1, - 0 (+ 25.40)	+ 1¼, - 0 (+ 31.75)
Over 6 to 9 (152.40 to 228.60), incl	+ 1¼, - 0 (+ 31.75)	+ 1½, - 0 (+ 38.10)
Over 9 to 12 (228.60 to 304.80), incl	+ 1½, - 0 (+ 38.10)	+ 2, - 0 (+ 50.80)

  

Machine Cut After Machine Straightening		
To 3 (76.20), incl	+ ⅞, - 0 (+ 3.18)	+ ⅜, - 0 (+ 4.76)
Over 3 to 6 (76.20 to 152.40), incl	+ ⅜, - 0 (+ 4.76)	+ ¼, - 0 (+ 6.35)
Over 6 to 9 (152.40 to 228.60), incl	+ ¼, - 0 (+ 6.35)	+ ⅝, - 0 (+ 7.94)
Over 9 to 12 (228.60 to 304.80), incl	+ ½, - 0 (+ 12.70)	+ ½, - 0 (+ 12.70)

TABLE 11 Camber for Hot-Rolled and Cold-Finished Titanium Bars for Machining

NOTE 1—Camber is the greatest deviation of a side from a straight line. Measurement is taken on the concave side of the bar with a straightedge. Unless otherwise specified, hot-rolled and cold-finished bars for machining purposes are furnished machine straightened to the tolerances specified in this table.

	Tolerance
Hot rolled	⅛ in. (3.18 mm) in any 5 ft (1524 mm), but may not exceed ⅛ × No. of ft in length 5
Cold finished	⅙ in. (1.59 mm) in any 5 ft (1524 mm), but may not exceed ⅙ × No. of ft in length 5

conforming retest results shall be reported to the purchaser. If the results for the retest fail to conform to the specification, the material will be rejected in accordance with Section 14.

12. Referee Test and Analysis

12.1 In the event of disagreement between the manufacturer and the purchaser on the conformance of the material to the requirements of this specification, a mutually acceptable referee shall perform the tests in question. The referee's testing shall be used in determining conformance of the material to this specification.

13. Rounding-Off Procedure

13.1 For purposes of determining conformance with the specifications contained herein, an observed or a calculated value shall be rounded off to the nearest "unit" in the last right-hand significant digit used in expressing the limiting value. This is in accordance with the round-off method of Practice E 29.

14. Rejection

14.1 Material not conforming to this specification or to authorized modifications shall be subject to rejection. Unless otherwise specified, rejected material may be returned to the manufacturer at the manufacturer's expense, unless the purchaser receives, within three weeks of notice of rejection, other instructions for disposition.

15. Certification

15.1 If so requested by the purchaser, the manufacturer shall supply at least one copy of his report certifying that the material supplied has been inspected and tested in accordance with the requirements of this specification and that the results of chemical analysis and mechanical tests meet the requirements of this specification for the appropriate grade.

16. Packaging and Package Marking

16.1 *Marking*—Unless otherwise specified, individual pieces or bundles shall have attached a metal tag stamped with the purchase order number, the specification number, the nominal size and manufacturer's heat number, or shall be boxed and the box marked with the same information. In addition to the above identification, bars 1 in. (25.4 mm) and over in diameter or distance between parallel sides shall be stamped with the heat number within 2 in. (50.8 mm) of one end.

16.2 *Packaging*—Unless otherwise specified, material purchased under this specification may be packaged for shipment either by boxing, crating, single boarding, burlapping, or with no protection in accordance with the manufacturer's standard practice.

17. Keywords

17.1 bar; billet; titanium; titanium alloy

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

L. Sc  
1.1  
metal  
spong  
chunl  
1.2  
R600  
chara  
sectic  
must  
cross  
1.3  
gain  
units  
state  
syste  
cann  
1.4  
safet  
respc  
priat  
bility  
2. R  
2.1  
E.  
I  
3. T  
3.1  
3.1  
600  
3.1  
3.1  
Reacti  
Subco  
Cur  
approv